

MECHSTER™ 1110G

(Isophthalate Polyester Gelcoat Resin)

Mechster™ designates a variety of unsaturated polyester resins synthesized at **Mechemco Industries**. These resins are specially engineered to meet the most diverse needs of fibreglass reinforced plastic moulding industry. Our R & D is geared to tailor **Mechster™ Resins** for the customers' most specific end application. In fact we take pride in suitably formulating the resin to improve your production efficiency as also the field performance of the FRP product.

Mechster™ 1110G is a gelcoat resin which is a thixotropic version of Isophthalate Polyester Resin, **Mechster™ 1110**.

Mechster™ 1110G is designed to have :

- Excellent surface finish
- Faster curing time
- Easier Vertical surface applications
- Minimal Sagging
- Excellent toughness

Component made from **Mechster™ 1110G** exhibit excellent surface finish which is smooth and glossy. This provides very good hydrolytic stability, improved mechanical strength and electrical insulation properties.

Physical Properties

Appearance	: Opaque Liquid
Specific Gravity @30°C	: 1.12 ± 0.01
Viscosity @ 30°C by Brookfield Viscometer	
RVT, Sp. No. 5, 50 rpm, cP	: 4200 ± 200
Thixotropic Index (10/100) rpm:	5.0 ± 0.5
Acid Value mg KOH/g	: 15 ± 3
Volatile Content (w/w) %	: 38 ± 2

Curing Behaviour

Gel time, minutes @ 30°C	: 7 ± 2
1.0 % Accelerator (Cobalt Octoate with 3% Co)	
2.0% Catalyst (MEKP with 8% Active Oxygen)	
Peak Exotherm Temperature, °C	: 175 ± 10

Properties of Cured Mechster™ 1110G

Specific Gravity @ 30°C	: 1.20
Tensile Strength, MPa	: 80
Tensile Modulus, MPa	: 3800
Elongation at Break, %	: 3.5
Flexural Strength, MPa	: 125
Flexural Modulus, MPa	: 4000
Heat Deflection Temperature, °C	: 85
Barcol Hardness	: 45
(Test methods : IS 6746-1972, ASTM and BS where IS not available.)	

Uses

Mechster™ 1110G is a suitable gelcoat for use along with **Mechster™ 1110** for all types of FRP hand layup and spray techniques.

Packing

Mechster™ 1110G is supplied in non returnable M.S. drums containing 225 kgs. net and HDPE carboys containing 35 kgs. net.

Storage

Mechster™ 1110G should be stored in a cool and dry place away from sunlight, preferably below 25°C. Under these conditions, the shelf life is 3 months. The storage stability could be further improved by aerating the resin stored in barrels at an interval of about a fortnight.

Handling

Mechster™ 1110G has a flash point of 34°C and is classified as flammable. Containers should be kept in a cool and ventilated place away from sunlight and sources of ignition. "No Smoking" rules should be strictly enforced. In case of fire, use dry chemical, foam, carbon dioxide or water spray to extinguish the flame. Spillages may be absorbed onto sand or earth and shovelled off and disposed according to local disposal regulations.

Caution

Store catalyst and accelerator separately. Do not allow them to come in contact with each other as they form an explosive mixture. Carry out separate addition of accelerator and catalyst to the resin mix for avoiding accidents.

Physiological and Toxicological Behaviour of Mechster™ 1110G

Skin contact and vapor inhalation should be avoided during moulding because of the presence of styrene monomer. In case of irritation in the eye or skin, wash with copious amount of water. In extreme case, seek immediate medical advice. The moulding area should be sufficiently ventilated for reducing the vapour levels in the air while compounding and moulding.

The above information and recommendation are based on our extensive experience in the field and is provided only as a general guidance for application of our product. The user should verify the suitability of our product for their own specific applications. We do not warrant or assume any liability for the information provided.

UV Stabilized Version is also available upon request

Mechster™ is the Registered Trade Mark of Mechemco Industries

Office: 27, Kewal Industrial Estate, Senapati Bapat Marg, Lower Parel, Mumbai 400 013. INDIA

Tel: +91-22-2495 1799, 2492 2039, **FAX:** +91-22-2494 5907

Web Site: www.mechemco.com **E-Mail:** mechemco@vsnl.com

Works: A-34, MIDC, Phase II, Dombivli (East), Pin 421 204. INDIA

Tel: +91-251-2871998, **Tel Fax:** +91-251-2871356