



MECHSTER™ 1110NG(T)

(NPG-Isophthalate Tooling Gelcoat)

Mechster™ designates a variety of unsaturated polyester resins synthesized at **Mechemco Industries**. These resins are specially engineered to meet the most diverse needs of fibreglass reinforced plastic moulding industry. Our R & D is geared to tailor **Mechster™ Resins** for the customers' most specific end application. In fact we take pride in suitably formulating the resin to improve your production efficiency as also the field performance of the FRP product.

Mechster™ 1110NG(T) is a specially formulated tooling gelcoat resin which is modified using NPG-Isophthalate Polyester Resin, **Mechster™ 1110N**. The very smooth surface is obtained with this gel coat. This gel coat can be easily mixed with color paste for desired color

Mechster™ 1110NG(T) is designed to have :

- Excellent surface finish
- Excellent Toughness and good abrasion resistance
- Excellent adhesion with the backup FRP
- Easier Vertical surface applications with virtually no sagging

Component made from **Mechster™ 1110NG(T)** exhibit excellent surface finish which is smooth and glossy. This provides very good hydrolytic stability, improved mechanical strength and electrical insulation properties desired in the tooling application.

Physical Properties

Appearance	: Highly Viscous Opaue Liquid
Specific Gravity @25 °C	: 1.20 ± 0.01
Viscosity @ 25°C by Brookfield Viscometer, cps	: Thixotropic
Acid Value mg KOH/g	: 11 ± 3
Volatile Content (w/w) %	: 35 ± 2

Curing Behaviour

Gel time, minutes @ 25°C	: 15 - 20
1.5 % Accelerator (Cobalt Octoate with 3% Co)	
1.5% Catalyst (MEKP with 8% Active Oxygen)	
Peak Exotherm Temperature, °C	: 130-135

Properties of Cured Mechster™ 1110NG(T)

Specific Gravity @ 25°C	: 1.26
Tensile Strength, MPa	: 55
Tensile Modulus, MPa	: 3200
Flexural Strength, MPa	: 120
Flexural Modulus, MPa	: 3400
Elongation at Break, %	: 3.5
Heat Deflection Temperature, °C	: 105
Barcol Hardness	: 45
(Test methods : IS 6746-1994, ASTM and BS where IS not available.)	

Uses

Mechster™ 1110NG(T) is a suitable tooling gelcoat for all types of moulds to be used for Hand-layup, Spray-up and RTM applications. The material is best suitable for precision moulding. This tooling gel coat can be backed up with Tooling Resin - **Mechster™ 1110(T)** for best results.

Packing

Mechster™ 1110NG(T) is supplied in non returnable M.S. drums containing 25 kgs. And 50 kgs net

Storage

Mechster™ 1110NG(T) should be stored in a cool and dry place away from sunlight, preferably below 25°C. Under these conditions, the shelf life is 3 months. The storage stability could be further improved by aerating the resin stored in barrels at an interval of about a fortnight.

Handling

Mechster™ 1110NG(T) has a flash point of 34°C and is classified as flammable. Containers should be kept in a cool and ventilated place away from sunlight and sources of ignition. "No Smoking" rules should be strictly enforced. In case of fire, use dry chemical, foam, carbon dioxide or water spray to extinguish the flame. Spillages may be absorbed onto sand or earth and shovelled off and disposed according to local disposal regulations.

Caution

Store catalyst and accelerator separately. Do not allow them to come in contact with each other as they form an explosive mixture. Carry out separate addition of accelerator and catalyst to the resin mix for avoiding accidents.

Precautions for Handling Mechster™ 1110NG(T)

Skin contact and vapor inhalation should be avoided during moulding because of the presence of styrene monomer. In case of irritation in the eye or skin, wash with copious amount of water. In extreme case, seek immediate medical advice. The moulding area should be sufficiently ventilated for reducing the vapour levels in the air while compounding and moulding.

The above information and recommendation are based on our extensive experience in the field and is provided only as a general guidance for application of our product. The user should verify the suitability of our product for their own specific applications. We do not warrant or assume any liability for the information provided.

Office: 27, Kewal Industrial Estate, Senapati Bapat Marg, Lower Parel, Mumbai 400 013. INDIA

Tel: +91-22-495 1799, 492 2039, **FAX:** +91-22-494 5907

Web Site: www.mechemco.com **E-Mail:** mechemco@vsnl.com

Works: A-34, MIDC, Phase II, Dombivli (East), Pin 421 204. INDIA

Tel: +91-251-871998 **Tele-fax:** +91-251-871356