

Mechster™ 1110TA

(Pre-accelerated Thixotropic Isophthalate Polyester Resin)

Mechster™ designates a variety of unsaturated polyester resins synthesized at **Mechemco Industries**. These resins are specially engineered to meet the most diverse needs of fibreglass reinforced plastic moulding industry. Our R & D is geared to tailor **Mechster™ Resins** for the customers' most specific end application. In fact we take pride in suitably formulating the resin to improve your production efficiency as also the field performance of the FRP product.

Mechster™ 1110TA is a specially designed pre-accelerated, thixotropic Isophthalate Polyester Resin, suitable for high performance FRP applications

Mechster™ 1110TA is designed to have :

- Excellent surface finish
- Faster curing time with even curing
- Easier Vertical surface applications
- Minimal Sagging

Component made from **Mechster™ 1110TA** exhibit excellent surface finish which is smooth and glossy. This provides very good hydrolytic stability, improved mechanical strength and electrical insulation properties.

Physical Properties

Appearance	: Hazy Rose Color Liquid
Specific Gravity @25°C	: 1.10 ± 0.01
Viscosity @ 25°C by Brookfield Viscometer	
RVT, Sp. #2, 50 rpm, cP	: 550 ± 100
Thixotropic Index	: 2.0
Acid Value mg KOH/g	: 15 ± 3
Volatile Content (w/w) %	: 40 ± 2

Curing Behaviour

Gel time, minutes @ 25°C with 1.5% MEKP (9% Active Oxygen)	: 15 - 20
Peak Exotherm Temperature, °C	: 180-190

Properties of Cured Mechster™ 1110TA

Specific Gravity @ 25°C	: 1.20
Tensile Strength, MPa	: 75
Tensile Modulus, MPa	: 3600
Elongation at Break, %	: 3.0
Flexural Strength, MPa	: 125
Flexural Modulus, MPa	: 3800
Heat Deflection Temperature, °C	: 95
Barcol Hardness	: 40

(Test methods : IS 6746-1972, ASTM and BS where IS not available.)

Uses

Mechster™ 1110TA is a suitable thixotropic resin for a single step multi layered built up using hand lay-up and spray-up techniques. This results in the resin material savings.

Packing

Mechster™ 1110TA is supplied in non returnable M.S. drums containing 225 kgs. net and HDPE carboys containing 35 kgs. net.

Storage

Mechster™ 1110TA should be stored in a cool and dry place away from sunlight, preferably below 25°C. Under these conditions, the shelf life is 3 months. The storage stability could be further improved by aerating the resin stored in barrels at an interval of about a fortnight.

Handling

Mechster™ 1110TA has a flash point of 34°C and is classified as flammable. Containers should be kept in a cool and ventilated place away from sunlight and sources of ignition. "No Smoking" rules should be strictly enforced. In case of fire, use dry chemical, foam, carbon dioxide or water spray to extinguish the flame. Spillages may be absorbed onto sand or earth and shovelled off and disposed according to local disposal regulations.

Skin contact and vapor inhalation should be avoided during moulding because of the presence of styrene monomer. In case of irritation in the eye or skin, wash with copious amount of water. In extreme case, seek immediate medical advice. The moulding area should be sufficiently ventilated for reducing the vapour levels in the air while compounding and moulding.

The above information and recommendation are based on our extensive experience in the field and is provided only as a general guidance for application of our product. The user should verify the suitability of our product for their own specific applications. We do not warrant or assume any liability for the information provided.